

**THIS PAGE IS INSERTED BY OIPE SCANNING
AND IS NOT PART OF THE OFFICIAL RECORD**

Best Available Images

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

BLACK BORDERS ✓

TEXT CUT OFF AT TOP, BOTTOM OR SIDES

FADED TEXT

BLURRY OR ILLEGIBLE TEXT

SKEWED/SLANTED IMAGES

COLORED PHOTOS HAVE BEEN RENDERED INTO BLACK AND WHITE

VERY DARK BLACK AND WHITE PHOTOS

UNDECIPHERABLE GRAY SCALE DOCUMENTS

**IMAGES ARE THE BEST AVAILABLE
COPY. AS RESCANNING *WILL NOT*
CORRECT IMAGES, PLEASE DO NOT
REPORT THE IMAGES TO THE
PROBLEM IMAGE BOX.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G21K 4/00, C09K 11/85	A1	(11) International Publication Number: WO 96/01479 (43) International Publication Date: 18 January 1996 (18.01.96)
(21) International Application Number: PCT/EP95/01077 (22) International Filing Date: 21 March 1995 (21.03.95) (30) Priority Data: 94201931.6 5 July 1994 (05.07.94) EP (34) Countries for which the regional or international application was filed: AT et al. (71) Applicant (for all designated States except US): AGFA-GEVAERT NAAMLOZE VENNOOTSCHAP [BE/BE]; Septestraat 27, B-2640 Mortsel (BE). (72) Inventor; and (75) Inventor/Applicant (for US only): LEBLANS, Paul [BE/BE]; Agfa-Gevaert N.V., DIE 3800, Septestraat 27, B-2640 Mortsel (BE).		(81) Designated States: JP, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: PHOTOSTIMULABLE PHOSPHOR SCREEN SUITED FOR DUAL ENERGY RECORDING		
(57) Abstract A single sheet photostimulable phosphor screen, characterized in that said screen contains in consecutive order (1) a support, (2) a continuous phosphor-containing layer, and permanently and contiguously united therewith (3) a grid structured phosphor-containing layer containing a phosphor different from the phosphor contained in said continuous phosphor-containing layer (2), said grid structured layer (3) containing parallel rows of phosphor-containing stripes or dots, and said different phosphors having a different X-ray absorption capacity with respect to different energy levels of X-ray radiation.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

PHOTOSTIMULABLE PHOSPHOR SCREEN SUITED FOR DUAL ENERGY RECORDING

1. Field of the Invention

The present invention relates to a single sheet photostimulable phosphor screen suited for dual energy recording of an X-ray pattern containing X-rays of different energy level.

2. Background of the Invention

Substances showing the phenomenon of luminescence under the influence of X-rays are called phosphors.

According to a classical method of recording and reproducing X-ray images X-ray absorbing phosphor particles are used in phosphor panels or screens to form radiographs in photographic silver halide emulsion materials sensitive to the fluorescent light promptly emitted by the phosphors where struck by X-rays.

In another radiographic method the principles of which are disclosed in US-P 3,859,527 photostimulable phosphors are used. Said method comprises the exposure to X-rays of a photostimulable phosphor panel which phosphor stores at least part of the energy of the incident X-rays. At some interval after the exposure, a beam of visible or infra-red light scans the panel to stimulate the release of stored energy as light that is detected and converted into sequential electrical signals which are processable to produce a visible image.

According to the periodical Radiology, September 1983, p. 834 the imaging plate containing a photostimulable phosphor can be used repeatedly to store X-ray images simply by flooding it with light in order to erase the residual energy contained.

In the medical X-ray field it is often necessary to provide information on soft tissue structures and bone-like structures simultaneously. For that purpose "dual-energy" techniques operating in a single shot X-ray exposure with a low energy absorbing front screen and a high energy absorbing back screen separated by X-ray beam hardening filter have been used in classical screen-film assemblage exposure as well as in X-ray imaging with photostimulable storage phosphor screens (ref. Dev P. Chakraborty and Gary T. Barnes in Med. Phys. 16 (1), Jan/Feb 1989, p. 7).

The production of low- and high-energy images that are acquired simultaneously avoids image misregistration between the low- and

high-energy exposures that could occur by patient-motion.

For the front screen preferentially absorbing the low-energy X-ray photons, useful in the imaging of the structure of soft tissue, low atomic number phosphors are used, whereas the higher energy part of the X-ray beam giving more information on the bone structure is absorbed or stopped in a back screen containing a higher atomic number phosphor.

In the above mentioned periodical Med. Phys. 16 (1), p. 7-8 an energy sensitive cassette for dual-energy mammography has been described wherein the back imaging plate contains a commercial barium fluorobromide phosphor and the front plate contains a similar but no commercially available strontium fluorobromide phosphor. The selection of these phosphors has been made in view of the K edges of Ba and Sr being respectively 37.4 and 16.1.

The K edge of Ba ensures high absorption efficiency of the barium fluorobromide phosphor above 38 keV, whereas the strontium fluorobromide is absorbing effectively in the X-ray region with energies from 15 to 25 keV.

In order to make that the lower energy X-ray radiation cannot interfere with the Ba-type phosphor an interscreen filter, also called midfilter in the form of a copper sheet is used (ref. Medical Physics, Vol. 17, No. 4, Jul/Aug 1990, p.667).

The following phosphor combinations for classical screen-film dual energy X-ray recording were considered : SrFBr/BaFBr, $\text{Y}_2\text{O}_2\text{S}/\text{Gd}_2\text{O}_2\text{S}$ and $\text{Y}_2\text{O}_2\text{S}/\text{LuTaO}_4$.

In US-P 5,051,589 a stimuable phosphor sheet suited for subtraction radiography is described wherein different stimuable phosphors are mixed together or take the form of a layer, wherein at least a first stimuable phosphor is represented by the formula $\text{GdOCl}:\text{Ce}$ and a second stimuable phosphor is represented by the formula $\text{SrFCl}:\text{Eu}^{2+}$. Said phosphors have different X-ray absorption characteristics which represent different absorptivity with respect to energy levels of X-ray radiation and have different response speeds with regard to stimulating rays which cause them to emit light in proportion to the amounts of X-ray energy stored.

In published European patent application 0 112 469 corresponding with US-P 4,855,598 an X-ray pattern subtraction method is described comprising the steps of :

(i) obtaining at least two X-ray images of an object including a specific structure exhibiting radiation energy absorption characteristics different from the radiation energy absorption

- characteristics of the other structure in said object.
- (ii) extracting an image of said specific structure by subtraction of one of said images from the other one, characterized by
 - (iii) simultaneously exposing a plurality of stimuable phosphor sheets (A,B; A,B,B'; A,B,C) which are overlaid one upon another to provide a composite member, to the X-ray radiation passing through said object, to store radiation images in the respective stimuable phosphor sheets (A,B; A,B,B'; A,B,C) so that image information is recorded in a stimuable phosphor sheet (B; B,B';B,C) positioned farther from said object in such a way that, at least at the area of the record corresponding to said specific structure, a low energy component of the radiation is recorded at a lower intensity than in a stimuable phosphor sheet (A) positioned closer to said object.
 - (iv) scanning the respective stimuable phosphor sheets (A,B; A,B,B'; A,B,C) with stimulating rays to sequentially release the radiation energy stored in the stimuable phosphor sheets as light emission.
 - (v) photoelectrically detecting the emitted light and converting it to digital image signals representing the respective X-ray radiation images.
 - (vi) providing at least two sets of digital image signals, representing at least two respective X-ray radiation images, for use in subtraction processing, and
 - (vii) extracting an image of said specific structure by subtraction processing of said sets of signals, i.e. multiplying digital image signals of corresponding picture elements by weight factors and subtracting said weighted signals.

For the use in image subtraction of weight factors for bones and soft tissue reference is also made to US-P 5,049,748.

As described by John M. Boone, Melvin Tecotzky and Guillermo M. Alexander in the article "Binary Screen Detector System for Single-Pulse Dual-Energy Radiography" published in the periodical Radiology, June 1992; p. 863 the read out and digitization of images obtained from stacked detector screens during imagewise X-ray exposure proceeds after separation of the stacked elements. During that separation and separate read out the spatial alignment between the images and detectors may be lost.

Published European patent application 0 126 564 and corresponding US-P 4,752,557 relates to a radiation image storage panel and its preparation in which a photostimulable phosphor is provided on a substrate with a honeycomb structure constituted of a

number of cells partitioned by wall members filled with the stimuable phosphor. According to said documents the radiation image storage panel can give images of markedly improved sharpness.

The use of said panel in separately recording a higher and lower energy level pattern from a single X-ray pattern has neither been disclosed nor suggested in said US-P 4,752,557.

3. Objects and Summary of the Invention

It is an object of the present invention to provide a single sheet photostimulable phosphor screen suited for yielding a higher and lower energy level pattern from a single X-ray pattern and suited for forming a subtraction pattern without misregistration.

It is another object of the present invention to provide a "dual-energy" recording technique operating with said single sheet phosphor screen in a single shot X-ray exposure avoiding problems of misregistration in recording of higher and lower energy level X-ray patterns and in their reading out in the form of photostimulated light.

Other objects and advantages of the present invention will become clear from the following description and drawing.

The present invention provides a single sheet photostimulable phosphor screen, characterized in that said screen contains in consecutive order (1) a support, (2) a continuous phosphor-containing layer, and permanently and contiguously united therewith (3) a grid structured phosphor-containing layer containing a phosphor different from the phosphor contained in said continuous phosphor-containing layer (2), said grid structured layer (3) containing parallel rows of phosphor-containing stripes or dots, and said different phosphors having a different X-ray absorption capacity with respect to different energy levels of X-ray radiation.

In a first modified embodiment of said single sheet photostimulable phosphor screen said continuous phosphor-containing layer (2) has been replaced by a phosphor-containing layer (4) having a grid structure and wherein the grid structured layers (3) and (4) each have parallel rows of phosphor-containing stripes or dots spatially arranged in such a way that the rows of phosphor-containing layer (3) are not overlapping with the rows of phosphor-containing layer (4), and phosphor(s) of said layer (3) is (are) different from phosphor(s) of said layer (4) by having different X-ray absorption capacity with respect to different energy levels of

X-ray radiation.

In a second modified embodiment of said single sheet photostimulable phosphor screen said continuous phosphor-containing layer (2) has been replaced by a phosphor-containing layer (4) having a grid structure and wherein the grid structured layers (3) and (4) each have parallel rows of phosphor-containing stripes or dots spatially arranged in such a way that the rows of phosphor-containing layer (3) are crossing the rows of phosphor-containing layer (4), and phosphor(s) of said layer (3) is (are) different from phosphor(s) of said layer (4) by having different X-ray absorption capacity with respect to different energy levels of X-ray radiation.

Further in accordance with the present invention an X-ray radiation recording process is provided comprising the consecutive steps of :

(1) exposing a single sheet phosphor screen to an X-ray pattern obtained by passing X-rays of different energy level through an object, said phosphor screen being a phosphor screen according to the present invention as described above,

(2) separately scanningwise photostimulating the different phosphors in said single sheet phosphor screen,

(3) separately photo-electronically detecting the fluorescent light emitted by said different phosphors and providing two sets of digital image signals corresponding with the detected fluorescent light levels, and optionally

(4) extracting an image of specific structure by subtraction processing of said sets of signals.

4. Brief Description of the Drawings

In the accompanying Fig. 1 to 3 cross-sectional views are given respectively of the above mentioned main embodiment and first modified embodiment of a single sheet photostimulable phosphor screen according to the present invention.

In the accompanying Fig. 4 a top view is given of a single sheet photostimulable phosphor screen according to the above mentioned second modified embodiment of the present invention.

5. Detailed Description of the Invention

As illustrated in Fig. 1 according to the main embodiment of the present invention a single sheet photostimulable phosphor screen

contains a transparent support 1 coated with a transparent subbing layer 2. Photostimulating phosphor particles 4 dispersed in polymeric binder 5 are present in a continuous (common) phosphor layer 3. Said phosphor layer 3 stands in permanent contact with a gridlike structure in the form of parallel stripes 6 containing photostimulable phosphor particles 7 different from photostimulable phosphor particles 4 in a polymeric binder 8. Optionally said relief structure has been coated with a uniformly applied light-transparent covering layer 9 serving as protective coating filling the voids between the stripes 6.

The photostimulable phosphors contained in said phosphor layer 3 and in said parallel stripes 6 have a different X-ray absorption capacity with respect to different energy levels contained in an X-ray pattern.

As illustrated in Fig. 2 a phosphor screen according to the present invention contains a transparent self-supporting layer 10 having at one side parallel grooves 11 filled with a phosphor-binder mixture 12 and at the opposite side parallel grooves 13 filled with another phosphor-binder mixture 14, the phosphor present in the grooves at one side of said self-supporting layer being different from the phosphor present in the grooves of the opposite side of said self-supporting support.

The grooves 11 and 13 are formed e.g. by milling and do not overlap or overlap only partially (dotwise) by crossing each other.

The photostimulable phosphors contained respectively in said grooves 11 and 13 have a different X-ray absorption capacity with respect to different energy levels contained in an X-ray pattern.

Optionally the inner walls of the grooves (11 and 13) are provided, e.g. by vapor deposition, with an opaque material absorbing or reflecting photostimulating light (excitation light), e.g. the innerwalls are provided with vapor-deposited aluminium giving them a mirror finishing by which the light emitted by photostimulation is reflected, improving thereby the sensitivity of the system.

As illustrated in Fig. 3 a phosphor screen according to the present invention 8 contains a transparent support (i) indicated by numeral 20 having parallel grooves 25 filled with a phosphor-binder mixture 22, which transparent support (i) has been laminated through a thin clear adhesive layer 24 with a transparent self-supporting layer (ii) indicated by numeral 23 which self-supporting layer (ii) has parallel grooves 21 filled with a phosphor-binder mixture 26.


The photostimulable phosphors contained respectively in said grooves 21 and 25 have a different X-ray absorption capacity with respect to different energy levels contained in an X-ray pattern.

Fig. 4 illustrates by top view an embodiment of a single sheet photostimulable phosphor screen having crossing grooves 30 and 31 in which the photostimulable phosphors are different. Scanningwise read out of such screen proceeds by photostimulating the phosphor particles contained in grooves 30 along the axis of said grooves whereby a continuous (linetype) signal is obtained. Scanningwise read out of the phosphor particles contained in the grooves 31 in a direction perpendicular to the grooves 31 yields a discontinuous (dotype) signal.

According to a preferred embodiment of a single sheet photostimulable phosphor screen according to the present invention one of said phosphor-containing layers contains a photostimulable phosphor mainly containing barium as host metal and the other phosphor-containing layer contains a photostimulable phosphor mainly containing strontium as host metal.

Thus, in a "dual energy" recording method according to the present invention the higher energy level X-rays are absorbed preferably by a photostimulable phosphor mainly containing barium as host metal whereas the lower energy level X-rays are absorbed by a photostimulable phosphor mainly containing strontium as host metal. For example, said phosphor is a Eu^{2+} doped barium fluorohalide as described e.g. in US-P 4,239,968, EP 0 021 342, EP 0 345 903 or in published European patent application 0 533 233.

A preferred photostimulable phosphor mainly containing strontium as host metal is a phosphor corresponding to the following empirical formula (I):



wherein :

x is in the range $0 \leq x \leq 0.10$, preferably $0 \leq x \leq 0.03$;

y is in the range $0 \leq y \leq 0.10$, preferably $0 \leq y \leq 0.03$;

a is in the range $0 \leq a \leq 1.30$, preferably $0.8 \leq a \leq 1.20$;

b is in the range $0 \leq b \leq 1$;

z is in the range $10^{-7} \leq z \leq 0.15$, and

A is Eu^{2+} or Eu^{2+} together with one or more of the co-dopants selected from the group consisting of Eu^{3+} , Y, Tb, Ce, Tm, Dy, Pr, Ho, Nd, Yb, Er, La, Gd and Lu.

Preferably in said phosphor fluorine is present stoichiometrically in a larger atom % than bromine or chlorine taken alone or bromine combined with chlorine.

A photostimulable phosphor according to said empirical formula (I) can be prepared by using as starting materials :

- (1) strontium fluoride;
- (2) magnesium halide optionally in combination with calcium halide (the halide can be partially fluoride in combination with chloride and/or bromide);
- (3) a strontium halide (including strontium chloride and bromide);
- (4) at least one A containing compound selected from the group consisting of europium halide, europium oxide, europium nitrate and europium sulphate, optionally in admixture with at least one of Y, Tb, Ce, Tm, Dy, Pr, Ho, Nd, Yb, Er, La, Gd and Lu oxides or salt, preferably fluorides.

Preferably the preparation proceeds by using ammonium halide, e.g. NH_4Br , NH_4Cl and/or NH_4I in the firing mixture as a co-reactant for introducing in the phosphor the halide ion of the ammonium salt.

The preparation of said phosphor may proceed analogously to the preparation of the barium(strontium)fluorohalide phosphor described in European patent 345 903.

The firing of the above halides proceeds preferably at temperatures between 650 and 850 °C in a reducing atmosphere. The reducing atmosphere is a mixture of hydrogen with inert gas, e.g. argon or nitrogen or is formed in situ by reaction of charcoal and water vapour to form a mixture of hydrogen and carbon monoxide or hydrogen and carbon dioxide, and/or by the use of an ammonium halide.

The reducing atmosphere reduces most or all of the present trivalent europium to divalent europium.

After the firing is completed the product obtained is pulverized. The pulverized product may be further fired. Multiple firing may be advantageous to improve the homogeneity and stimulation properties of the phosphor.

Other phosphors with relatively low K edge value are the following :

1. $\text{M}^{\text{I}}\text{X}$: $x\text{Bi}$, wherein M^{I} = Rb and X = Cl, Br and/or I;
2. RbX : $x\text{Tl}$, wherein X = Br and/or I;
3. YOX : $z\text{A}$, wherein X = Cl and/or Br and A = Ce or Tb;

4. $\text{Sr}_3(\text{PO}_4)_2 : \text{Eu}^{2+}$;
5. $\text{Sr}_5(\text{PO}_4)_3\text{X} : x\text{Eu}^{2+}$;
6. $\text{Sr}_2\text{PO}_4\text{X} : x\text{Eu}^{2+}$;
7. $\text{Sr}_2\text{M}^{\text{II}}\text{Si}_2\text{O}_7 : x\text{Ce}^{3+}$;
8. $\text{Sr}_5\text{SiO}_4\text{X}_6 : \text{Eu}^{2+}$, wherein X is halogen;
9. $\text{Y}_2\text{SiO}_5 : a\text{Tb}, b\text{Ce}$;
10. $\text{Y}_2\text{SiO}_5 : \text{Ce}^{3+}, \text{Sm}^{3+}$;
11. $\text{Sr}_2\text{BO}_3\text{X} : x\text{Eu}^{2+}$, wherein X = Cl, Br and/or I;
12. $\text{Sr}_{2-x}(\text{B}_5\text{O}_9)_{5-y/2}\text{X}_y : \text{D}_x$, X is halogen and D = $\text{Eu}^{2+}, \text{Ce}^{3+}$;

The photostimulable phosphor particles applied according to the present invention may have an average grain size in the range of 1 to 30 μm , the larger grains offering a better sensitivity but less image resolution. It is not preferred to use phosphor particles having a grain size larger than the width of the line structures or diameter of the dot structures.

In the production of a "dual energy" phosphor panel the photostimulable phosphors are used preferably in dispersed state in a polymeric organic binder although some phosphors such as the alkali metal halide phosphors disclosed e.g. in (PCT) WO 87 004177 can be applied by vacuum-deposition.

Suitable binders for forming a binder layer incorporating the photostimulable phosphor in dispersed form are film forming organic polymers, e.g. a cellulose acetate butyrate, polyalkyl (meth)acrylates, e.g. poly(methyl methacrylate), a polyvinyl-n-butyral e.g. as described in the United States Patent Specification 3,043,710, a copoly(vinyl acetate/vinyl chloride) and a copoly(acrylonitrile/butadiene/styrene) or a copoly(vinyl chloride/vinyl acetate/vinyl alcohol) or mixture thereof.

In view of the sensitivity and sharpness of the radiation image storage panel containing photostimulable phosphor particles dispersed in a binder, the binder should preferably be present in an amount as small as possible, but is normally within the range from 0.03 to 0.2 parts by weight with respect to the binder content.

The coverage of the phosphor is preferably in the range from about 300 to 1500 g/m^2 . The thickness of the continuous phosphor layer and of the relief structure of the grid structured phosphor layer is preferably in the range of 0.05 to 0.5 mm.

The dimensions of the phosphor-containing portions and interstitial portions (lines or dots) of the grid structured screen layers are as small as possible for obtaining a high image

resolution. In practice the depth of the cells filled with phosphor or phosphor-binder mixture is 30 to 1000 μm , the width of the cells is preferably within the range of 10 to 600 μm and the width (thickness) of the partitioning wall members is preferably in the range of 10 to 300 μm (ref. US-P 4,752,557).

The continuous phosphor layer of the photostimulable dual energy phosphor panel according to the present invention is coated on a support sheet by coating techniques known to those skilled in the art.

The production of the grid structured phosphor layers may proceed in different ways.

According to a first embodiment a grid structured phosphor layer for use in a photostimulable phosphor screen according to the present invention is formed by filling the grooves or pits of a transparent resin support with a phosphor-binder mixture. The grooves or pits can be obtained by casting the resin material in a mother mold as described e.g. in published European patent application 0 126 564 and corresponding US-P 4,752,557, which documents as DE 4,142,150 relate to grid structured phosphor screens produced through molding. In another way the grooves are obtained by milling a continuous hardened phosphor coating that is removed linewise mechanically leaving a linewise relief of the phosphor coating.

According to a second embodiment a structured phosphor layer for use in a photostimulable phosphor screen according to the present invention is formed according to a technique described in DE 39 09 450 wherein a fine metalgrid is filled with phosphor particles or a phosphor-binder mass. The supported grid-structures are covered with a protective transparent foil, e.g. foil of polyimide. Such screens have a very good mechanical stability and life time. The metallic separating walls of these "chambered" phosphor structures have a thickness of about 5 μm , a height of about 300 μm and the micro-chambers filled with phosphor have an inner diameter of about 30 μm .

According to a third embodiment a grid structured phosphor layer is obtained using a peel-off or wash-off technique combined with a phosphor resin binder or composition that is photosoluble or photohardenable.

Photoresist resin binders suitable for forming pigmented relief structures are known for the production of photopolymer printing plates as described e.g. by Kurt I. Jacobson - Ralph E. Jacobson in

the book "Imaging Systems" - The Focal Press - London and New York (1976), p. 181-222.

Suitable support materials for use in the production of dual energy panels according to the present invention are made of a film forming organic resin, e.g. polyethylene terephthalate, but paper and cardboard supports optionally coated with a resin layer such as an alpha-olefinic resin layer are also particularly useful. Further glass and metal supports are used in certain circumstances.

For producing a photostimulable phosphor coating composition the phosphor particles are intimately dispersed in a solution of film-forming resin binder in an organic solvent, e.g. 2-methoxy-propanol or ethyl acetate. The coating of said composition may proceed according to any usual technique, e.g. by spraying, dip-coating or doctor blade coating. After coating, the solvent(s) of the coating mixture is (are) removed by evaporation, e.g. by drying in a hot (60°C) air current.

Solvent-less coating may be carried out by using UV or electron beam (EB) curable binder compositions as described e.g. in Research Disclosure December 1977, item 16435.

An ultrasonic treatment can be applied to improve the packing density and to perform the de-aeration of the phosphor-binder combination. Before the optional application of a protective coating the phosphor-binder layer may be calendered to improve the packing density (i.e. the number of grams of phosphor per cm³ of dry coating).

Optionally, a light-reflecting layer is provided on the support to enhance the output of light emitted by photostimulation. Such a light-reflecting layer may contain white pigment particles dispersed in a binder, e.g. titanium dioxide particles, or it may be made of a vapour-deposited metal layer, e.g. an aluminium layer, or it may be a coloured pigment layer absorbing stimulating radiation but reflecting the emitted light as described e.g. in US-P 4,380,702.

Optionally a light-absorbing layer is provided on the support or in the support itself to avoid reflection and scattering of light at the interface of the support and the most close phosphor-containing layer, thereby increasing the image resolution of the photostimulable phosphor screen.

Since in the above described X-ray recording system operating with photostimulable radiographic screens the screens are used repeatedly, it is important to provide them with an adequate topcoat for protecting the phosphor-containing layers from mechanical and

chemical damage. This is particularly important for photostimulable radiographic screens where each screen normally is not encased in a cassette.

A protective layer can be coated onto the outermost phosphor-containing layer or relief structure by directly applying thereto a coating solution containing a film-forming organic solvent-soluble polymer such as nitrocellulose, ethylcellulose or cellulose acetate or poly(meth)acrylic resin and removing the solvent by evaporation. According to another technique a clear, thin, tough, flexible, dimensionally stable polyamide film is bonded to the phosphor layer as described in published EP 00 392 474.

According to a further known technique a protective overcoat is produced with a radiation-curable composition. Use of a radiation curable coating as protective top layer in a X-ray conversion screen is described e.g. in EP 209 358 and JP 86/176900 and US-P 4,893,021. For example, the protective layer comprises a UV cured resin composition formed by monomers and/or prepolymers that are polymerized by free-radical polymerization with the aid of a photoinitiator. The monomeric products are preferably solvents for the prepolymers used.

The photostimulation of the Eu^{2+} doped barium fluorohalide or strontium fluorohalide phosphor proceeds with good X-ray conversion efficiency results with light in the wavelength range of 450 to 650 nm. The emitted fluorescent light produced by photostimulation has a peak wavelength at about 390 nm. Particularly useful photostimulating light emitting light sources for the scanningwise reading out of the dual energy phosphor panels according to the present invention are e.g. the frequency doubled (532 nm) solid state Nd-YAG laser, an argon ion laser wherefrom either the 488 nm line or 514.5 nm emission line is used, and a He-Ne gas laser emitting at 633 nm.

The X-ray energy stored in the photostimulable phosphors having different X-ray absorption capacity with respect to different energy levels contained in the applied X-ray pattern are read out either simultaneously or sequentially.

Sequential read out of the different phosphor layers of the single phosphor sheet or panel according to the present invention may proceed using encoder marks on the phosphor panel in order to direct a first laser beam scanningwise on the area of the phosphor sheet or panel covered by the phosphor having higher absorption

capacity for higher energy X-rays, and to direct thereupon a second laser beam on the area of the phosphor panel covered by the phosphor having absorption capacity primarily for the lower energy level X-rays of the X-ray exposure pattern.

So, according to a particular embodiment a single sheet phosphor screen according to the present invention contains separate tracks of encoder marks for controlling the position of a first and second read out laser beam used for reading out separately and sequentially said different phosphors after their exposure to an X-ray pattern.

The sequential read out of the different X-ray energy patterns proceeds preferably from the same side of the phosphor panel or sheet and may proceed by moving the phosphor sheet or panel to-and-fro under laser beam scanning optics and photo-electronic detection optics.

The encoder marks are optically detectable and may be perforations, optical windows or light-reflecting pits or spots forming separate code tracks in the panel that control separately the position of the first and second read out laser beams. The use of coder tracks for the positioning of a laser beam is known from optical disk technology and is described e.g. in US-P 4,400,443.

Scanningwise read out of a photostimulable phosphor sheet by means of laser beam and photoelectronic detection is illustrated in Fig. 1 of published European Patent Application 0 532 800.

Simultaneous read out of a phosphor panel may proceed e.g. by exposing the continuous phosphor layer illustrated in Fig. 1 through the transparent support from the rear side of the panel and the grid structured phosphor layer from the front side, optionally using the same laser source and mirror optics for deflecting the laser light scanningwise to said front and rear side.

In order to make that reflected stimulating light does not enter the photo-electronic detector together with emitted fluorescent light (stimulated light) filter means are used which may be cut-off filters, transmission bandpass filters and band-reject filters. A survey of filter types and spectral transmittance classification is given in SPSE Handbook of Photographic Science and Engineering, Edited by Woodlief Thomas, Jr. - A Wiley-Interscience Publication - John Wiley & Sons, New York (1973), p. 264-326.

Shortwave pass filters that transmit the shorter wavelengths and reject the longer wavelengths are listed in Table 4.12 of said SPSE Handbook.

Bandpass filters that transmit or reject only a limited band of

wavelengths are listed in Tables 4.13 and 4.14 respectively. Tables of many selected long-wave, shortwave pass, and bandpass filters, both liquid and solid, for wavelengths from 150 to 3500 nm, are given by W. Summer, Photo Sensitors, Chapman & Hall, London, 1957, chap. 9.

The fluorescent light emitted by photostimulation is detected preferably with a transducer transforming light energy into electrical energy, e.g. a phototube (photomultiplier) providing sequential electrical signals that can be digitized and stored. After storage these signals can be subjected to digital processing. Digital processing includes e.g. image contrast enhancement, spatial frequency enhancement, image subtraction, image addition and contour definition of particular image parts.

According to one embodiment for the reproduction of the recorded X-ray image the optionally processed digital signals are transformed into analog signals that are used to modulate a writing laser beam, e.g. by means of an acousto-optical modulator. The modulated laser beam is then used to scan a photographic material, e.g. silver halide emulsion film whereon the X-ray image optionally in image-processed state is reproduced.

According to another embodiment the digital signals obtained from the analog-digital conversion of the electrical signals corresponding with the light obtained through photostimulation are displayed on a cathode-ray tube. Before display the signals may be processed by computer. Conventional image processing techniques can be applied to reduce the signal-to-noise ratio of the image and enhance the image quality of coarse or fine image features of the radiograph.

CLAIMS

1. A single sheet photostimulable phosphor screen, characterized in that said screen contains in consecutive order (1) a support, (2) a continuous phosphor-containing layer, and permanently and contiguously united therewith (3) a grid structured phosphor-containing layer containing a phosphor different from the phosphor contained in said continuous phosphor-containing layer (2), said grid structured layer (3) containing parallel rows of phosphor-containing stripes or dots, and said different phosphors having a different X-ray absorption capacity with respect to different energy levels of X-ray radiation.


2. Phosphor screen according to claim 1, with the modification that said continuous phosphor-containing layer (2) has been replaced by a phosphor-containing layer (4) having a grid structure and wherein the grid structured layers (3) and (4) each have parallel rows of phosphor-containing stripes or dots spatially arranged in such a way that the rows of phosphor-containing layer (3) are not overlapping with the rows of phosphor-containing layer (4), and phosphor(s) of said layer (3) is (are) different from phosphor(s) of said layer (4) by having different X-ray absorption capacity with respect to different energy levels of X-ray radiation.

3. Phosphor screen according to claim 1, with the modification that said continuous phosphor-containing layer (2) has been replaced by a phosphor-containing layer (4) having a grid structure and wherein the grid structured layers (3) and (4) each have parallel rows of phosphor-containing stripes or dots spatially arranged in such a way that the rows of phosphor-containing layer (3) are crossing the rows of phosphor-containing layer (4), and phosphor(s) of said layer (3) is (are) different from phosphor(s) of said layer (4) by having different X-ray absorption capacity with respect to different energy levels of X-ray radiation.

4. Phosphor screen according to any of the preceding claims, wherein one of said phosphor-containing layers contains a photostimulable phosphor mainly containing barium as host metal and the other phosphor-containing layer contains a photostimulable phosphor mainly containing strontium as host metal.

5. Phosphor screen according to claim 4, wherein said phosphor containing barium as host metal is a Eu^{2+} doped barium fluorohalide.

6. Phosphor screen according to claim 4 or 5, wherein said phosphor mainly containing strontium as host metal corresponds to the following empirical formula (I):



wherein :

x is in the range $0 \leq x \leq 0.10$;

y is in the range $0 \leq y \leq 0.10$;

a is in the range $0 \leq a \leq 1.30$;

b is in the range $0 \leq b \leq 1$;

z is in the range $10^{-7} \leq z \leq 0.15$, and

A is Eu^{2+} or Eu^{2+} together with one or more of the co-dopants selected from the group consisting of Eu^{3+} , Y, Tb, Ce, Tm, Dy, Pr, Ho, Nd, Yb, Er, La, Gd and Lu.

7. Phosphor screen according to claim 2 or 3, wherein said phosphor screen contains a transparent self-supporting layer having at one side parallel grooves filled with a phosphor-binder mixture and at the opposite side parallel grooves filled with another phosphor-binder mixture, the phosphor present in the grooves at one side of said self-supporting layer being different from the phosphor present in the grooves of the opposite side of said self-supporting support.

8. Phosphor screen according to claim 2 or 3, wherein said phosphor screen contains a transparent support (i) having parallel grooves filled with a phosphor-binder mixture, which transparent support (i) has been laminated together with a transparent self-supporting layer (ii) also having parallel grooves filled with a phosphor-binder mixture, the phosphor present in the grooves of support (i) being different from the phosphor present in the grooves of said self-supporting layer (ii).

9. Phosphor screen according to claim 7 or 8, wherein said grooves have inner walls that are provided with an opaque material absorbing or reflecting photostimulating light.

10. Phosphor screen according to claim 9, wherein said opaque material reflecting photostimulating light is vacuum-deposited aluminium.

11. Phosphor screen according to any of the preceding claims, wherein said screen contains separate tracks of encoder marks for controlling the position of a first and second read out laser beam used for reading out separately and sequentially said different phosphors after there exposure to an X-ray pattern.

12. An X-ray radiation recording process comprising the consecutive steps of :

(1) exposing a single sheet phosphor screen to an X-ray pattern obtained by passing X-rays of different energy level through an object, said phosphor screen being a single sheet phosphor screen according to any of the claims 1 to 10.

(2) separately scanningwise photostimulating the different phosphors in said single sheet phosphor screen.

(3) separately photo-electronically detecting the fluorescent light emitted by said different phosphors and providing two sets of digital image signals corresponding with the detected fluorescent light levels, and optionally

(4) extracting an image of specific structure by subtraction processing of said sets of signals.




FIG. 1




FIG. 2




FIG. 3




FIG. 4

INTERNATIONAL SEARCH REPORT

International / .cation No

PCT/EP 95/01077

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G21K4/00 C09K11/85

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G21K C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP-A-0 411 194 (SCHOTT GLASWERKE) 6 February 1991 see claims 1-19 ---	1,2,4-6
A	EP-A-0 536 830 (PHILIPS') 14 April 1993 see claims 1-17 ---	1,2
A	EP-A-0 240 053 (PHILIPS') 7 October 1987 see claims 1-20 ---	1,2
A	FR-A-2 462 020 (SIEMENS) 6 February 1981 see claims 1-8 ---	1,2
A	EP-A-0 520 094 (AGFA-GEVAERT) 30 December 1992 see claims 1-14 ---	5
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

24 July 1995

Date of mailing of the international search report

28.07.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Drouot, M-C

INTERNATIONAL SEARCH REPORT

International / cation No

PCT/EP 95/01077

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP-A-0 159 015 (FUJI PHOTO) 23 October 1985 see claims 1-15 ---	6
A	EP-A-0 168 057 (FUJI PHOTO) 15 January 1986 see claims 1-27 -----	6

INTERNATIONAL SEARCH REPORT

Information on patent family members

International / Publication No

PCT/EP 95/01077

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0411194	06-02-91	NONE	
EP-A-0536830	14-04-93	JP-A- 5217528 US-A- 5367155	27-08-93 22-11-94
EP-A-0240053	07-10-87	NL-A- 8600696 JP-A- 62235600 US-A- 4820926	16-10-87 15-10-87 11-04-89
FR-A-2462020	06-02-81	DE-A- 2929745 JP-B- 2047056 JP-A- 56022029 US-A- 4371806	29-01-81 18-10-90 02-03-81 01-02-83
EP-A-0520094	30-12-92	NONE	
EP-A-0159015	23-10-85	JP-C- 1589350 JP-B- 2014394 JP-A- 60221484 US-A- 4894548	30-11-90 06-04-90 06-11-85 16-01-90
EP-A-0168057	15-01-86	JP-C- 1815401 JP-B- 5026835 JP-A- 61023679 JP-C- 1815402 JP-B- 5026836 JP-A- 61023680 US-A- 4698508	18-01-94 19-04-93 01-02-86 18-01-94 19-04-93 01-02-86 06-10-87